

Petrothene®

LM600500

High Density Polyethylene

Blow Molding Grade

Melt Index 0.35 Density 0.960+

Applications

PETROTHENE LM600500 resin is especially designed for water, milk and juice bottles. LM600500 exhibits excellent rigidity and good processability.

Regulatory Status

LM600500 meets the requirements of the Food and Drug Administration regulation 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information.

Processing Techniques

Specific recommendations for processing LM600500 can be made only when the processing conditions, equipment and end use are known. For further suggestions, contact your Equistar sales representative.

Typical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index	0.35	g/10 min	D 1238
Density	0.960+	g/cc	D 1505
Tensile Strength @ Break	4,400	psi	D 638
Elongation @ Break	>600	%	D 638
Flexural Modulus	220,000	psi	D 790
Tensile Impact	100	ft-lb/in.	D 1822
Low Temperature Brittleness, F ₅₀	<-76	°C	D 746
Heat Deflection Temperature @ 66 psi	78	°C	D 648
Vicat Softening Point	125	°C	D 1525
Hardness, Shore D	68		D 2240

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at 800.700.0946.

® Petrothene is a registered trademark of Equistar Chemicals, LP..



Lyondell Chemical Company
1221 McKinney, Suite 700
P.O. Box 2583
Houston, Texas 77252-2583
800.615.8999
<http://www.equistarchem.com>