

Petrothene®

NA345

Low Density Polyethylene

Film Extrusion Grade

Melt Index 1.8 Density 0.921

Applications

PETROTHENE NA345 is a series of homopolymer resins that combine premium clarity with strength and stiffness. In addition, NA345 exhibits good impact strength on both flat and creased film. NA345 is recommended for textile packaging, light produce, bread bags and other thin packaging films enhanced by clarity and sparkle. The optical values of NA345 actually improve with decreases in film gauge and are maintained at wide die gap settings. This fact leads to important cost savings. Film can be drawn down to a minimum gauge consistent with required physical properties, with the assurance that optical properties will not suffer, but improve. With wider die gaps back pressures are reduced, as are extrusion costs.

Regulatory Status

The basic resin NA345 meets the requirements of the Food and Drug Administration, regulation 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for further information.

Processing Techniques

Specific recommendations for processing NA345 can only be made when the processing conditions, equipment and end use are known. For further suggestions please contact your Equistar sales representative.

Typical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index	1.8	g/10 min	D 1238
Base Resin Density	0.921	g/cc	D 1505
Vicat Softening Point	100	°C	D 1525
Film*			
Haze ¹	5.0	%	D 1003
Gloss, 45° ¹	70	units	D 2457
Dart Drop impact Strength, F ₅₀	90	g	D 1709
Tensile Strength @ Yield, TD	1,600	psi	D 882
Tensile Strength @ Break, MD (TD)	4,000 (3,400)		
Elongation, MD (TD)	300 (500)	%	D 882
1% Secant Modulus, MD (TD)	26,000 (30,000)	psi	D 882
Elmendorf Tear Strength, MD (TD)	360 (200)	g	D 1922

Product	NA345013	NA345184	NA345196	NA345245X01
Slip	0	0	750	1,500
Antiblock	0	1,500	1,600	6,000

These are typical values and are not to be construed as specific product limits.

* Data obtained from film produced in a 3½" (89 mm) blown film line, commercially available 8" (203 mm) die, 375°F (191°C) melt extrusion temperature 2:1 BUR, 1.25 mil (32 micron) gauge, 0.025" die gap at 130 lb/hr.

¹ Optical properties given for NA345196 (medium slip, medium antiblock)

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at 800.700.0946.

® Petrothene is a registered trademark of Equistar Chemicals, LP.



Lyondell Chemical Company
1221 McKinney, Suite 700
P.O. Box 2583
Houston, Texas 77252-2583
800.615.8999
<http://www.equistarchem.com>