

**Petrothene®**

# NA940

**Low Density Polyethylene**
**Film Extrusion Grade**
**Melt Index 0.25 Density 0.918**

## Applications

PETROTHENE NA940 is a series of resins designed for heavy duty film applications. Superior puncture resistance combined with excellent impact properties make NA940 an ideal choice for bags used to package fertilizer, peat moss, decorative stone and agricultural and construction materials.

## Typical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index	0.25	g/10 min	D 1238
Base Resin Density	0.918	g/cc	D 1505
Vicat Softening Point	90	°C	D 1525
<b>Film*</b>			
Dart Drop Impact Strength, F <sub>50</sub>	220	g	D 1709
Tensile Strength, MD (TD)	3,000 (2,800)	psi	D 882
Elongation, MD (TD)	300 (500)	%	D 882
1 % Secant Modulus, MD (TD)	24,000 (27,000)	psi	E 111
Elmendorf Tear Strength, MD (TD)	220 (200)	g	D 1922
<b>Molding</b>			
Low Temperature Brittleness, F <sub>50</sub>	<-76	°C	D 746
Tensile Strength @ Break	2,100	psi	D 638
Elongation @ Break	>600	%	D 638
Flexural Modulus	34,000	psi	D 790
Hardness, Shore D	50		D 2240
Environmental Stress Crack Resistance, # Failures in 100% Igepal®	0 in 7 days		D 1693
<b>Products</b>			
	<b>NA940000</b>	<b>NA940085</b>	<b>NA940094</b>
Slip	None	None	Low
Antiblock	None	High	High

These are typical values and not to be construed as specific product limits.

\* Data obtained from film produced in a 3½" (89 mm) blown film line, commercials available 8" (203 mm) die, 430°F (221°C) melt extrusion temperature, 2:1 BUR, 2 mil (51 micron) gauge, 0.025" die gap at 170 lb/hr.

® Igepal is a registered trademark of the Rhone -Poulenc Co., Inc.

See Page 2 for Additional Information

**Petrothene®****NA940****Low Density Polyethylene****Film Extrusion Grade****Melt Index 0.25 Density 0.918****Regulatory  
Status**

The basic resin NA940 meets the requirements of the Food and Drug Administration regulation, 21 CFR 177.1520. This regulation allows the use of this olefin polymer'... in articles or components of articles intended for use in contact with food.' Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information regarding the suitability of specific products for specific applications.

**Processing  
Techniques**

NA 940 has been designed for excellent processability, bubble stability and good heat sealing over a wide range of extrusion conditions. Optimum properties are found at melt temperatures of 330°-430°F (165°-221°C) and blow-up ratios between 1.8:1 and 2.5:1. Drawdown to 1.5 mil (38.1 microns) is possible at commercial rates when proper extrusion techniques are used. Specific recommendations for processing NA 940 can be made only when the end use applications, required properties and processing equipment are known. For exact recommendations, contact your Equistar sales representative.

---

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at 800.700.0946.

® Petrothene is a registered trademark of Equistar Chemicals, LP.



Lyondell Chemical Company  
1221 McKinney, Suite 700  
P.O. Box 2583  
Houston, Texas 77252-2583  
800.615.8999  
<http://www.equistarchem.com>